

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : B01J 27/08, 23/02, C07C 29/50, 31/04	A1	(11) International Publication Number: WO 00/07718 (43) International Publication Date: 17 February 2000 (17.02.00)
(21) International Application Number: PCT/EP99/05576 (22) International Filing Date: 30 July 1999 (30.07.99) (30) Priority Data: MI98A001847 5 August 1998 (05.08.98) IT (71) Applicant (for all designated States except US): ENITEC-NOLOGIE S.P.A. [IT/IT]; Via F. Maritano, 26, I-20097 San Donato Milanese (IT). (72) Inventors; and (75) Inventors/Applicants (for US only): BELLUSSI, Giuseppe [IT/IT]; Via Scoto, 44, I-29100 Piacenza (IT). PEREGO, Carlo [IT/IT]; Via S.S. Cornelio e Cipriano, 15/E, I-20040 Carnate (IT). ZANIBELLI, Laura [IT/IT]; Via. F. Donati, I, I-26013 Crema (IT). (74) Agents: DE GREGORI, Antonella et al.; Ing. Barzano' & Zanardo, Milano S.p.A., Via Borgonuovo, 10, I-20121 Milan (IT).		(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: CATALYST AND PROCESS FOR THE OXIDATION OF METHANE TO METHANOL (57) Abstract Catalytic composition, optionally supported on an inert material, characterized in that it comprises (i) oxides and/or hydroxides of a first metal (M1) and (ii) halides of a second metal (M2), wherein M1 and M2, the same or different, are selected from metals belonging to groups IIa, IIb, IVb, VIII, Ib, Va, Lanthanides, and relative mixtures. Its preparation and use in the selective transformation of methane into methanol are also described.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

CATALYST AND PROCESS FOR THE OXIDATION OF METHANE TO METHANOL

The present invention relates to a catalytic composition, its preparation and its use in the process for transforming methane into methanol in a single step.

5 Methane is a raw material which is widely available, often however in remote places. The transportation costs are therefore very high and its compression to liquid which is easier to transport can only take place under extreme temperature and pressure conditions.

10 Consequently, owing to the high availability of natural gas and its localisation in geographically remote places, the possibility of finding a way of converting it directly in loco to products which can be transported at a lower cost, is definitely of great interest.

15 Attention is therefore directed towards hydrocarbon products with a higher molecular weight or to oxygenated products. One of these products could be methanol, which is used as both an intermediate product for chemicals and a possible energy vector.

20 The activation of methane however is not easy owing to the strong stability of the C-H bond with respect to higher hydrocarbons; processes using oxidation reactions are therefore normally adopted.

Even in well consolidated catalytic processes such
25 as steam reforming to syngas ($\text{CO} + \text{H}_2$), it is necessary

to operate under high temperature conditions ($T > 700^{\circ}\text{C}$) and to avoid the formation of the by-product CO_2 . The numerous studies being carried out (for example oxidative coupling and oxidation in homogeneous phase) have not led
5 to industrial embodiments.

Alternatively, the activation of methane takes place either by oxidation or by halogenation or a combination of the two processes (oxy-halogenation). The most favoured products in the first case are CO_x , in the second
10 case halogen-derivatives. In both cases subsequent treatment is necessary to obtain the desired products.

As far as methanol is concerned, this is industrially produced by means of two catalytic steps: the first consists in the steam reforming reaction to give syngas
15 ($\text{CO} + \text{H}_2$), the second in the actual formation reaction of methanol, after regulating the optimum CO/H_2 ratio.

As a rule methanol can be produced starting from methane by means of two types of processes: a direct process, in which the methane is transformed into methanol in a single step; an indirect process, in which the
20 reaction takes place in several steps, i.e. a first activation step of methane and one (or more) subsequent steps for the actual production of methanol.

Typical examples of direct processes are:

25 a) Casey et al. In Ind. Eng. Chem. Res. (1994) who de-

scribe a non-catalytic process at 350-550°C and at 50 bars, with a yield to methanol of 1.8%;

b) Hunter, Gesser et al. in Appl. Cat. 1990, who describe a non-catalytic process at 350°C and 30 bars with a
5 yield to methanol of 7%;

c) Hunter, Gesser et al. in Appl. cat. 1990, who describe a catalytic process with $\text{SnO}_2/\text{Cu}/\text{SiO}_2$ at 250°C and 30 bars with a yield to methanol of 3.3%;

d) Chun, Anthony in Ind. Eng. Chem. Res. (1993) who de-
10 scribes a non-catalytic method at 430-500°C and 50 bars, with a yield to methanol of less than 2%;

e) Chun, Anthony in Ind. Eng. Chem. Res. (1993) who de-
scribes a catalytic method with CuMo (or FeMo) / SiO_2 at 430-500°C and 50 bars, with a yield to methanol of
15 less than 3%.

All these direct processes have the disadvantage of not reaching yields higher than 7%.

In this respect, it should be pointed out that, although the reaction ΔG of the oxidation of methane to
20 methanol is negative, the reaction ΔG s to CO and CO_2 are much more negative. This implies the necessity of operating with limited conversions of methane to keep the selectivity high or effecting quenchings of the newly-formed products to limit their subsequent oxidation.

25 A catalytic composition has now been found, which

overcomes the drawbacks mentioned above, as it allows methane to be converted to methanol in a single step with yields even higher than 7% and with selectivities higher than 90% to methanol.

5 In accordance with this, the present invention relates to a catalytic composition, optionally supported on an inert material, characterized in that it comprises (i) oxides and/or hydroxides of a first metal (M1) and (ii) halides of a second metal (M2), wherein M1 and M2, the
10 same or different, are selected from metals belonging to groups IIa, IIb, IVb, VIII, Ib, IIb, Va, Lanthanides, and relative mixtures.

The optional inert material supporting the catalytic composition is selected from metal oxides normally used
15 for this purpose, for example, aluminum, silicon, titanium, zirconium, cerium, lanthanum, preferably aluminum and silicon.

In the preferred embodiment, the oxides and/or hydroxides and halides are selected from oxides, hydroxides
20 and halides of Mg, Ca, Ba, La, Ni, Cu, Zn, Bi, even more preferably, Mg, Ba, Bi, Ni.

As far as the halides are concerned, these are preferably selected from chlorides, bromides and iodides, and are even more preferably bromides.

25 The catalytic composition of the present invention

is also characterized by a molar ratio $M1/M2 \geq 1$, preferably from 1 to 2..

The catalytic composition of the present invention can be prepared by means of various techniques known to
5 experts in the field, in particular by means of sol-gel synthesis, impregnation, physical mixing of oxides and/or hydroxides and halides.

In the case of sol-gel synthesis, the same metal halides or metal salts (for example nitrates, acetates,
10 oxalates) in the latter case in acid solution of hydrohalogen acid, can be introduced during the synthesis phase.

In particular, the sol-gel synthesis process illustrated hereunder for Silicon but applicable to any type of carrier, can be described as follows (it is assumed
15 that $M1=M2$ and that a salt of $M1$, different from the halide, soluble in alcohol, is used):

- a) a solution, normally alcohol, of a salt of the metal, is prepared;
- b) an organic source of Silicon is added to the solution of step (a);
20
- c) an aqueous solution of hydrohalogen acid is added to the solution of step (b), thus obtaining a gel;
- d) the gel of step (c) is aged at a temperature lower than 100°C , preferably at a temperature ranging from
25 10°C to 60°C ;

- e) the aged gel of step (d) is dried, preferably up to a temperature of 100°C;
- f) the gel of step (e) is calcined, preferably up to a maximum temperature of 300-500°C and even more preferably at a maximum temperature of 300-350°C, preferably in a stream of nitrogen.

It is obvious that when a metal halide is used in step (a), during step (c) it is sufficient to add water for the gelation to take place.

- Finally, when the metal salt of step (a) is insoluble in alcohol, it is dissolved in an aqueous solution, preferably acid by hydrohalogen acid, whereas the Silicon source in step (b) is put in an alcohol solution. The gelation takes place by the simple addition of the Silicon solution to the metal solution. With reference to this latter possibility, a simplified preparation scheme of the catalytic composition of the present invention can therefore be represented as follows:

Si precursor in alcohol + aqueous solution of the metal + HX --> hydrolysis --> ageing --> drying --> calcination.

When the synthesis of the supported oxides alone is effected, during step (c) an aqueous solution is added which is acid by HNO₃ or basic by the addition of an ammonium salt in relation to the precipitation pH of the

hydroxide, which produces the desired oxide during the calcination phase.

The materials thus obtained mainly consist of an amorphous carrier in which the halides and/or oxides-
5 hydroxides are uniformly dispersed.

Alternatively, the above compositions can be prepared by impregnation of the carrier with solutions of metal salts in acid solution by hydrohalogen acid, preferably selected from HBr and HCl.

10 In the case of preparation by impregnation, commercial carriers or carriers obtained by the sol-gel method, following the procedure described above, can be used.

The molar ratios used in the preparation of the catalytic composition of the present invention (again in
15 the case of the sol-gel system and assuming that $M_1=M_2$) are:

M/SiO_2 = from 0.05 to 0.40, preferably from 0.1 to 0.30;

$EtOH/SiO_2$ = from 1.8 to 4.5, preferably from 2.2 to
20 3.2;

$H_2O/EtOH$ = from 0.005 to 10, preferably from 0.01 to 4.6;

H_2O/SiO_2 = from 0.01 to 20, preferably from 0.04 to 10.5.

25 The same M/SiO_2 ratio applies when the impregnation

technique or commercial oxides are used.


The present invention also relates to a process for the preparation of methanol starting from methane and oxygen, preferably air, under catalytic conditions, characterized in that the methanol is produced directly in the presence of the catalytic composition defined above.



In the preferred embodiment, the process of the present invention is carried out in a continuous system, in a stream of methane and air, at pressures close to atmospheric pressure, at temperatures ranging from 250°C to 450°C, preferably from 300°C to 350°C, with a WHSV in methane ranging from 0.01 to 1 h⁻¹ and a CH₄/O₂ ratio higher than 1.8/1 or lower than 0.7/1 within the temperature range indicated, to avoid falling within explosive limits. H₂O, in vapour form, may optionally be fed, in a ratio CH₄/H₂O ranging from 0.1/1 to 3/1, preferably from 0.3 to 2.5.

Theoretical reaction schemes are provided hereunder, for the case of bivalent metals, on whose active sites the chemical species methane and oxygen are absorbed and transformed.

In these schemes M, selected from M1 and M2, represents the metal and X the halogen.

Scheme 1:






--




Scheme 2:




10 -----


--



Scheme 3:



--



The process of the present invention does not comprise feeding of the halogen (or organic halides) together with the reagent mixture, as described in 2-step processes (oxyhalogenation of methane and subsequent hydrolysis).

This results in a considerable advantage for environmental impact, and in a smaller volume of reagents in

circulation. On the other hand the halides favour the activation of methane and its subsequent transformation, limiting oxidation to CO_x . In addition their effect is maintained over a period of time as they are present in
5 the catalyst.

The process of the present invention can be effected in the presence of one or more catalytic beds.

According to an embodiment of the process of the present invention, the gaseous mixture is sent to a single catalytic bed containing the catalytic composition of
10 the present invention.

According to another embodiment, the CH_4/O_2 mixture is fed to a first catalyst containing the metal halide (with the consequent activation of the methane). The mixture from this first catalyst is then fed to a second catalyst containing the metal oxide, with the consequent
15 production of methanol.

It is possible to operate in two catalytic beds at temperatures ranging from 200°C to 500°C , preferably from
20 300°C to 360°C .

According to another embodiment, the first catalytic bed is put at a temperature ranging from 300°C to 360°C , whereas the second bed is put at a temperature ranging from 70°C to 150°C .

25 Under the assumption of operating in the presence of

two catalytic beds and that the first catalytic bed has possibly been either partially or totally transformed from halide to oxide (and the second from oxide to halide), the flow of reagents or catalytic beds can be inverted.

It is essential however for the mixture of CH_4/O_2 to be fed first of all to the catalyst containing the halide and subsequently to the catalyst containing the metal oxide.

The following examples provide a better understanding of the present invention.

In these examples, the synthesis molar ratios of the catalytic systems are:

$$\text{M}/\text{SiO}_2 = 0.1 - 0.26$$

$$\text{EtOH}/\text{SiO}_2 = 2.2 - 3.2$$

$$\text{H}_2\text{O}/\text{EtOH} = 0.01 - 4.6$$

$$\text{H}_2\text{O}/\text{SiO}_2 = 0.04 - 10.5$$

EXAMPLES

Examples of the catalytic systems with NiBr_2 , MgBr_2 , BiBr_3 , NiO , $\text{Ba}(\text{OH})_2$ are provided hereunder.

In evaluating the catalytic activity of the catalysts listed above, the catalytic activity is evaluated as follows:

$$\text{Conversion: } 100 * (\text{CH}_4\text{in} - \text{CH}_4\text{out}) / (\text{CH}_4\text{in})$$

$$\text{Selectivity: } 100 * (\text{CH}_3\text{OH}/\text{Tot.products})$$

EXAMPLE 1 - Preparation of catalyst A.

3.1 grams of NiBr_2 are dispersed in 13.64 grams of EtOH under stirring at 50°C . 19.78 grams of TES (tetraethylorthosilicate) and then 8.40 grams of H_2O are added
5 to this solution. The molar ratio Ni/Si is 0.15, whereas the molar ratio $\text{Br/Ni} = 2$. The solution is left under stirring at 50°C until gelation (about 48 hours). This is followed by the ageing phase at room temperature for 16 hours, and then the drying phase in an oven at atmospheric
10 pressure at 100°C for 1.5 hours. It is then calcined in muffle with the following temperature program: heating in N_2 to 340°C (5°C/min.); pause at 340°C for 3 hours; finally spontaneous cooling to room temperature.

The characteristics of catalyst A are indicated in
15 Table 1.

EXAMPLE 2 - Preparation of catalyst B

Catalyst B is prepared according to the procedure adopted in example 1 and using the same reagents as example 1 in the same molar ratio.

20 The characteristics of catalyst B are indicated in Table 1.

EXAMPLE 3 - Preparation of catalyst C

2.49 grams of $\text{MgC}_4\text{H}_{10}\text{O}_2$ (Magnesium Ethylate) are dispersed in 9.05 grams of EtOH under stirring at 50°C and
25 18.16 grams of TES followed by 20.6 grams of HBr 20% by

weight are then added.

The solution is left under stirring at 50°C until gelation (after about 53 hours). This is followed by the ageing phase at room temperature for 10 hours, and the
5 drying phase in an oven at atmospheric pressure at 100°C for 2 hours. It is then calcined in muffle with the same temperature program as example 1.

Molar ratio Mg/Si = 0.25; molar ratio Br/Mg = 2.

The characteristics of catalyst C are indicated in
10 Table 1.

EXAMPLE 4 - Preparation of catalyst D

5.869 grams of Bi(NO₃)₃ are dispersed in 9.14 grams of EtOH under stirring at 50°C; 15.23 grams of TES, 4.23 grams of H₂O and 17.20 grams of HBr 20% by weight are
15 added in order to this suspension. The suspension is left under stirring at 50°C until gelation (about 30 hours). The other steps are the same as those described in example 3.

Molar ratio Bi/Si = 0.20; molar ratio Br/Bi = 3.

20 The characteristics of catalyst D are indicated in Table 1.

EXAMPLE 5 - Preparation of catalyst E (NiO).

20 grams of Ni(OH)₂ are calcined in muffle at 600°C for 5 hours in air.

25 The characteristics of catalyst E are indicated in

Table 1.

EXAMPLE 6 - Preparation of catalyst F (BaO/SiO_2).

2.32 grams of Ba(OH)_2 are dispersed in 8.99 grams of EtOH under stirring at 5°C ; 13.94 grams of TES and then
5 4.05 grams of H_2O are added to this suspension and the mixture is acidified with HNO_3 at 35%. The suspension is left under stirring at 50°C until gelation (about 70 hours). This is followed by the drying and calcination procedure described in example 3, except that the calci-
10 nation temperature is 450°C .

The characteristics of catalyst F are indicated in Table 1.

EXAMPLE 7 - Catalytic activity of the catalytic composition (A+E).

15 The catalytic system consisting of two catalytic beds, is put in a quartz reactor using corindone (40 mesh) as filler. The first catalytic bed consists of 2.2 grams of catalyst A, granulated to 30/50 mesh and diluted with 1 cc of quartz 18 mesh; the second catalytic bed
20 consists of 1.02 grams of catalyst E (30/50 mesh). Once charged into the respective reactors, catalyst A is brought to 355°C for 1 hour in a stream of N_2 (30 ml/min) whereas catalyst E is maintained at 100°C in a stream of nitrogen (30 ml/min). At these temperatures, obtained by
25 exploiting the various heated zones of the oven in which

the reactor is situated, the N_2 is closed and CH_4 and air ($CH_4/O_2 = 3$) are then fed at a $WHSV = 0.1 \text{ h}^{-1}$ (referring to the methane).

EXAMPLE 8 - Catalytic activity of the catalytic composition (C + $Ba(OH)_2$).

2.31 grams of catalyst C and 1.23 grams of $Ba(OH)_2$ are treated as in example 7, except that catalyst C is brought to a temperature of 345°C and the $Ba(OH)_2$ to 75°C .

The catalytic activity is indicated in Table 2.

EXAMPLE 9 - Catalytic activity of the catalytic composition (D + $Ba(OH)_2$).

2.20 grams of catalyst D and 1.20 grams of $Ba(OH)_2$ are treated as in example 6, except for the $WHSV = 0.05 \text{ h}^{-1}$.

The activity of this catalytic composition is illustrated in Table 2.

COMPARATIVE EXAMPLE 10 - Catalytic activity of catalyst A.

1.02 grams of catalyst A alone, granulated to 30-50 mesh, are diluted and treated as in example 7, except that the oven is heated to a single temperature of 360°C and the $WHSV$ is equal to 0.3 h^{-1} . The activity of this catalyst is indicated in Table 2.

EXAMPLE 11 - Catalytic activity of the catalytic composition

tion (C + Ba(OH)₂).

2.31 grams of catalyst C and 1.23 grams of Ba(OH)₂ are mechanically mixed, granulated to 30-50 mesh and diluted as in example 7, except that the catalytic system
5 obtained by mixing is brought to a single temperature of 300°C and WHSV = 0.05 h⁻¹.

The activity of this catalytic composition is indicated in Table 2.

EXAMPLE 12 - Catalytic activity of the catalytic composition (C + F)
10

2.11 grams of catalyst C and 1.16 grams of catalyst F are mechanically mixed, granulated to 30-50 mesh, diluted as in example 7, except that the catalytic system obtained by mixing is brought to a single temperature of
15 300°C and WHSV = 0.06 h⁻¹. H₂O is then fed by means of a double piston pump at a flow-rate equal to 0.001 ml/h, sent to a preheater brought to 200°C where it is mixed in the form of vapour with the reagent gases before being sent to the reactor.

20 The activity of this catalytic composition is indicated in Table 2.

TABLE 1

		Cat A	Cat B	Cat C	Cat D	Cat E	Cat F
5	Surf.area	490	450	340	90	90	20
	M/SiO ₂	0.11	0.15	0.25	0.2	---	0.2
	Br/M	2	2	2	3	---	---
10	M	Ni	Ni	Mg	Bi	Ni	Ba

TABLE 2

15	Example	7	8	9	10c	11	12
	Catal.	A+E	C+Ba(OH) ₂	D+Ba(OH) ₂	A	C+Ba(OH) ₂	C+F
20	Conv.CH ₄	2.24	2.2	9	4	5.3	9.9
	Sel.CH ₃ OH	100	99.7	100	20	100	100
	Sel.CH ₃ Br	---	0.3	---	80	---	---
25							

The results of Table 2 demonstrate the capacity of the various catalytic systems of effecting the activation of methane under bland temperature conditions, with low conversions to methane but accompanied by almost total selectivity to methanol, especially in the case of the coupling of several catalytic systems, in particular the system $\text{BiBr}_3/\text{SiO}_2$ and $\text{Ba}(\text{OH})_2$ (example 9) and Mg/Ba (example 12).

CLAIMS

1. A catalytic composition, optionally supported on an inert material, characterized in that it comprises (i) oxides and/or hydroxides of a first metal (M1) and (ii) halides of a second metal (M2), wherein M1 and M2, the same or different, are selected from metals belonging to groups IIa, IIb, IVb, VIII, Ib, IIb, Va, Lanthanides, and relative mixtures.
2. The catalytic composition according to claim 1, wherein the inert material is selected from the oxides of aluminum, silicon, titanium, zirconium, cerium, lanthanum.
3. The catalytic composition according to claim 2, characterized in that the inert material is selected from the oxides of aluminum and silicon.
4. The catalytic composition according to claim 1, characterized in that M1 and M2, the same or different, are selected from Mg, Ca, Ba, La, Ni, Cu, Zn, Bi.
5. The catalytic composition according to claim 4, wherein M1 and M2, the same or different, are selected from Mg, Ba, Bi, Ni.
6. The composition according to claim 1, characterized in that the halides are selected from chlorides, bromides and iodides, and are preferably bromides.

7. The catalytic composition according to claim 1, wherein the molar ratio $M1/M2 \geq 1$, is preferably from 1 to 2.
8. A process for the preparation of the catalytic composition according to claim 1, said process being selected from sol-gel synthesis, impregnation, physical mixing of oxides and/or hydroxides and halides.
9. A process for the preparation of methanol starting from methane and oxygen, preferably air, under catalytic conditions, characterized in that the methanol is produced directly in the presence of the catalytic composition according to claim 1.
10. The process according to claim 9, characterized in that the preparation of methanol is carried out in a system in continuous, in a stream of methane and air, at pressures close to atmospheric pressure.
11. The process according to claim 10, characterized in that the temperature ranges from 250°C to 450°C, the molar ratio CH_4/O_2 is higher than 1.8/1 or less than 0.7/1 within the above temperature range, optionally in the presence of vapour, the molar ratio CH_4/H_2O being from 0.1/1 to 3/1.
12. The process according to claim 11, characterized in that the temperature ranges from 300°C to 350°C and

the molar ratio $\text{CH}_4/\text{H}_2\text{O}$ ranges from 0.3/1 to 2.5/1.

13. The process according to claim 10, characterized in that the mixture CH_4/O_2 is sent to a first catalytic bed, essentially containing the metal halide (i),
- 5 the mixture leaving the first catalytic bed subsequently being sent to a second catalytic bed essentially containing the oxide (ii).
14. The process according to claim 13, characterized in that the temperature of both catalytic beds ranges
- 10 from 200°C to 500°C, preferably from 300°C to 360°C.
15. The process according to claim 13, characterized in that the temperature of the first catalytic bed ranges from 300°C to 360°C, whereas the temperature of the second catalytic bed ranges from 70°C to
- 15 150°C.
16. The process according to claim 13, characterized in that the flow of reagents or catalytic beds can be inverted.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/EP 99/05576

A. CLASSIFICATION OF SUBJECT MATTER IPC 7 B01J27/08 B01J23/02 C07C29/50 C07C31/04		
According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED Minimum documentation searched (classification system followed by classification symbols) IPC 7 B01J C07C		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the international search (name of data base and, where practical, search terms used)		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 98 22414 A (DU PONT ;NAPPA MARIO JOSEPH (US); RAO V N MALLIKARJUNA (US)) 28 May 1998 (1998-05-28) page 5, line 27 - line 37 ---	1,4,5,7, 8
A	GB 1 244 001 A (ICI LTD.) 25 August 1971 (1971-08-25) page 1, line 42 - line 50 ---	9-14
A	EP 0 580 356 A (SUN CO INC R & M) 26 January 1994 (1994-01-26) --- -/--	9-12
<input checked="" type="checkbox"/> Further documents are listed in the continuation of box C. <input checked="" type="checkbox"/> Patent family members are listed in annex.		
* Special categories of cited documents : "A" document defining the general state of the art which is not considered to be of particular relevance "E" earlier document but published on or after the international filing date "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) "O" document referring to an oral disclosure, use, exhibition or other means "P" document published prior to the international filing date but later than the priority date claimed "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. "&" document member of the same patent family		
Date of the actual completion of the international search 29 November 1999		Date of mailing of the international search report 13/12/1999
Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040, Tx. 31 651 epo nl, Fax: (+31-70) 340-3016		Authorized officer Zuurdeeg, B

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 99/05576

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>DATABASE WPI Section Ch, Week 199702 Derwent Publications Ltd., London, GB; Class E17, AN 1997-019470 XP002124212 & RU 2 057 745 C (CARBON MATERIALS RES TECH CENTRE), 10 April 1996 (1996-04-10) abstract</p>	
A	<p>WO 94 09897 A (ANDINA ENERGIA) 11 May 1994 (1994-05-11)</p>	

INTERNATIONAL SEARCH REPORT

information on patent family members

International Application No

PCT/EP 99/05576

Patent document cited in search report		Publication date	Patent family member(s)		Publication date
WO 9822414	A	28-05-1998	EP 0946472	A	06-10-1999
GB 1244001	A	25-08-1971	NONE		
EP 0580356	A	26-01-1994	US 5414157	A	09-05-1995
			CA 2099229	A	21-01-1994
			JP 6199715	A	19-07-1994
RU 2057745	C	10-04-1996	NONE		
WO 9409897	A	11-05-1994	US 5334777	A	02-08-1994
			US 5243098	A	07-09-1993
			AT 180183	T	15-06-1999
			AU 669599	B	13-06-1996
			AU 5664794	A	24-05-1994
			BG 61911	B	30-09-1998
			BG 99616	A	30-04-1996
			CA 2148586	A	11-05-1994
			CZ 9501127	A	15-11-1995
			DE 69325032	D	24-06-1999
			DE 69325032	T	23-09-1999
			DE 667804	T	10-10-1996
			EP 0667804	A	23-08-1995
			ES 2084570	T	16-05-1996
			FI 952118	A	29-06-1995
			HU 72832	A	28-05-1996
			JP 2678089	B	17-11-1997
			JP 8502755	T	26-03-1996
			NO 951726	A	03-07-1995
			NZ 258677	A	26-01-1998
			PL 308759	A	21-08-1995
			RO 113314	A	30-06-1994